



小零件/磁铁

磁铁 环型/方型



型号(1代码·2D) — (3V) — (4T)
EAHCW25 — 6 — 1

■ 请按步骤①~④选择型号和参数后进行订购。




型号区分: 7 天发货
代码

■ 环形



EAHCW



磁化方向: 厚度方向

① N极划线或点

代码	材质	表面处理	耐热温度
EAHCW	钕磁铁	镀镍	80℃

型号		3V	4T	吸引力 N {kgf}	表面磁通密度 高斯[G]
1代码	2D	选择			
EAHCW	6	2	2	6.2 {0.6}	2600~2800
			3	8.0 {0.8}	3200~3400
			1	4.9 {0.5}	1600~1800
	8	3 4	2	7.8 {0.8}	2600~2800
			3	9.8 {1.0}	3200~3400
			5	14.3 {1.5}	3200~3800
			1	6.9 {0.7}	1700~1900
	10	3 4 5 6	2	10.8 {1.1}	2600~2800
			3	11.8 {1.2}	3200~3400
		4 5 6	5	18.8 {1.9}	3600~3800
			1	7.8 {0.8}	1500~1700
	12	4 5 6 8	2	13.7 {1.4}	2500~2700
			3	15.7 {1.6}	2900~3100
		4 6 8	5	23.3 {2.4}	3600~3800
			1	8.8 {0.9}	1600~1800
	14	6 8	2	19.6 {2.0}	2600~2800
			3	23.5 {2.4}	2900~3100
			5	36.0 {3.7}	3600~3800
	18	6 8 12	3	48.6 {5.0}	2900~3100
			1	10.8 {1.1}	1300~1500
	20	6 8 10 12	2	21.6 {2.2}	2200~2400
			3	33.3 {3.4}	2600~2800
		6 12	5	62.3 {6.3}	3600~3800
	25	6 8 10 12	1	12.7 {1.3}	1300~1500
			2	34.3 {3.5}	2100~2300
			3	58.8 {6.0}	2600~2800
		6 12	5	73.8 {7.5}	3400~3600
	30	12 5	5	98.5 {10.0}	3000~3200



■ 请按步骤①~④选择型号和参数后进行订购。

● MGLN 型号(1代码·2A) — (3B) — (4T) ● MGLF 型号(1代码·2T) — (3A) — (4B)
EAMLN10 — 5 — 1 MGLF10 — 30 — 60




型号区分: 7 天发货
代码

■ 方型




代码	材质	表面处理	耐热温度
EAMLN	钕磁铁	镀镍	80℃
EAMLF	铁氧体磁铁	—	300℃

钕磁铁 EAMLN




磁化方向: 厚度方向



① N极划线或点

铁氧体磁铁 EAMLF



型号		3B	4T	吸引力 N {kgf}	表面磁通密度 高斯[G]
1代码	2A				
EAMLN (钕磁铁)	3	3	5	2.8 {0.29}	4100~4300
	4	4	5	5.6 {0.57}	4300~4500
	5	5	5	8.9 {0.91}	4400~4600
	6	6	6	13.7 {1.4}	4500~4700
	8	8	6	23.2 {2.37}	4400~4600
			1	2.7 {0.28}	1700~1900
	10	5	2	8.5 {0.87}	3000~3200
			5	16.8 {1.71}	4200~4400
			1	6.5 {0.66}	1800~2000
		10	2	11.8 {1.2}	2500~2700
			8	39.3 {4.01}	4500~4700
	15	5	3	13.9 {1.42}	3100~3300
			5	23.7 {2.42}	4100~4300
			10	31.4 {3.2}	4700~4900
		10	3	23.9 {2.44}	2900~3100
			5	34.3 {3.5}	3300~3700
			10	61.4 {6.27}	4600~4800
	20	5	10	40.8 {4.16}	4600~4800
			5	47.7 {4.87}	3500~3700
		10	10	77.8 {7.94}	4700~4900
			15	69.7 {7.11}	3300~3700
	30	20	5	84.8 {8.65}	3100~3300
			30	110.8 {11.31}	3300~3700

型号		3A	4B	吸引力 N {kgf}	表面磁通密度 高斯[G]	A公差	B公差
1代码	2T						
EAMLF (铁氧体磁铁)	5	10	5	1.6 {0.16}	900~1100	±0.1	±0.1
		20	10	4.9 {0.50}		±0.1	±0.1
		30	20	9.8 {1.00}	1000~1200	±0.15	±0.15
		50	20	12.7 {1.30}		±1.2	±0.4
		30	30	21.6 {2.20}		±0.15	±0.15
		30	60	29.4 {3.00}		±0.6	±1.2
	10	30	20	17.7 {1.80}	1100~1400	±0.8	±0.4
		40	40	31.4 {3.20}		±0.8	±0.8

询价④种方式



官网 <http://www.srdfaa.com>
深圳市仕瑞达自动化设备有限公司



全国免费 400-966-3863
客服热线 0755-27926613