





型号(①代码·②D)
EAHXF10

■ 请按步骤①~②选择型号和参数后进行订购。



型号区分:
代码 7 天发货

■ 强力平面型



型号		L	M×P (粗牙)	吸引力 N {kgf}	表面磁通密度 高斯[G]	d1	d2	B
①代码	②D							
EAHXF	4	5	M2×0.4	1.5 {0.1}	2400~2800	2	3	2.5
	5			2.0 {0.2}	2600~3000	2.5	3.5	
	6	8	M3×0.5	5.9 {0.6}	2100~3000	4	5	3
	8			9.8 {1.0}	2300~3300	6	7	
	10	10	M4×0.7	20.6 {2.1}	2500~3600	8	9	4
	13			45.1 {4.6}	2500~3600	10	11	
	16	10	M5×0.8	89.2 {9.1}	3000~4400	12	14	5
	20			128.5 {13.1}	3200~4600	15	18	
	25	13	M6×1.0	225.5 {23.0}	3200~4600	18	23	



型号(①代码·②D)
EAHUMN10

■ 请按步骤①~②选择型号和参数后进行订购。




型号区分:
代码 7 天发货

■ 强力型



型号	①		②		耐热 温度	③	磁极	
	材质	表面处理	材质	表面处理		材质	正	反
EAHXU	SUM24L	—	钕磁铁	—	80℃	黄铜	N	S
EAHUM		无电解镀镍						
EAHUS	SUS416	—	钕磁铁	镀镍				
EAHUMN	SUM24L	无电解镀镍						
EAHUSN	SUS416	—						
EAHMH	SUM22	无电解镀镍	耐热钕磁铁					

①HXUMNH使用耐热粘接剂。



型号		L	M×P (粗牙)	EAHXU·EAHUM·EAHUS		EAHUMN		EAHUSN		EAHMH		d1	d2	B	H
①代码	②D			吸引力 N {kgf}	表面磁通密度 高斯[G]	吸引力 N {kgf}	表面磁通密度 高斯[G]	吸引力 N {kgf}	表面磁通密度 高斯[G]	吸引力 N {kgf}	表面磁通密度 高斯[G]				
(钕磁铁) EAHXU EAHUM EAHUS	4	5	M2×0.4	—	—	0.784 {0.08}	3100~3300	—	—	—	—	2.5	3	1	0.5
	5			—	—	1.37 {0.14}	3100~3300	—	—	—	—	3.5	4		
	6	8	M3×0.5	3.9 {0.4}	2100~2600	4.9 {0.5}	3100~3300	4.9 {0.5}	3100~3300	4.9 {0.5}	3100~3300	4	5	2	1.6
	8			5.9 {0.6}	2400~2600	8.8 {0.9}	3300~3600	8.8 {0.9}	3300~3600	8.8 {0.9}	3300~3600	5	6		
(钕磁铁) EAHUMN EAHUSN	10	10	M4×0.7	14.7 {1.5}	2700~2900	19.6 {2.0}	3800~4100	19.6 {2.0}	3800~4100	19.6 {2.0}	3800~4100	7	8	3	2.1
	13			34.3 {3.5}	2800~3100	44.1 {4.5}	4000~4300	44.1 {4.5}	4000~4300	44.1 {4.5}	4000~4300	9.5	11		
	16	10	M5×0.8	58.8 {6.0}	2900~3300	63.7 {6.5}	4000~4300	63.7 {6.5}	4000~4300	—	—	12.5	14	4	3.1
(耐热钕磁铁) EAHMH	20			98.1 {10.0}	2900~3400	107.9 {11.0}	4100~4400	107.9 {11.0}	4100~4400	—	—	16.5	18		
	25	15	M6×1.0	137.3 {14.0}	2900~3400	—	—	176.5 {18.0}	4500~4800	—	—	21.5	23	6	5.1



邮箱: Service@srdfaa.com



传真: 0755-8957-5523

SRO仕瑞达