




小零件·磁铁




■ 请按步骤①~③选择型号和参数后进行订购。



标准型
EAUB
EAUBN



短头型
EASUBN



代码		① ④		②		③	耐热 温度
标准型	短头型	材质	表面处理	材质	表面处理	材质	
EAUB	—	SUM24L	无电解镍镀	钴磁铁	—	* 黄铜 (C3604BD)	80℃
EAUBN	EAUBSN			铁磁铁	镀镍		




型号		③L (选择)	B	T	(ℓ)	d1	d2	t	E	吸引力 N {kgf}		表面磁通密度 高斯[G]	
① 代码	②M (粗牙螺紋)									钴磁铁	钕磁铁	钴磁铁	钕磁铁
(标准型) EAUB EAUBN	3	10	7	5	1.2	4	5	2	2	2.9 {0.3}	3.9 {0.4}	2100~2600	2700~3000
	4	10 15	8	6	1.5	5	6			3.9 {0.4}	6.8 {0.7}	2500~2900	3000~3500
	5	10 15 20	10	7	2	7	8	3	10.8 {1.1}	16.7 {1.7}	2700~2900	3600~3900	
	6	15 20 25	13			9.5	11		27.5 {2.8}	39.2 {4.0}	2800~3100	3800~4200	
	8	15 20 25	17	9	3	12.5	14	4	47.1 {4.8}	83.4 {8.5}	2900~3300	2900~3400	
	10	20 25	21			16.5	18		6	5	88.3 {9.0}		140.2 {14.3}
(短头型) EASUBN	4	10	14	3	1	10					32.1 {3.3}		1700~1900
	5	10 15 20	17	3		12.5		1			49.0 {5.0}		2400~2600
	6	15 20 25	19	3.5	2	14.5		1.5	—	—	78.4 {8.0}	—	2600~2800
	8	15 20 25 30	21	4		16.5		1.5			117.7 {12.0}		
	10	20 25 30 35	24	5	3	18.5		2	176.5 {18.0}	2800~3100			



■ 请按步骤①~②选择型号和参数后进行订购。



代码		①固定座	②聚氨酯	③磁铁	耐热 温度
外螺纹	内螺纹	材质	材质	硬度	
EAXX	EAXXH	SUS304	乙醚类 聚氨酯	肖氏 A90	钕磁铁 80℃
EAXXA	—			肖氏 A70	



■ 外螺纹型

型号		M×P (粗牙)	L	ℓ ₁	ℓ ₂	f	m	W	R	吸引力 N {kgf}	表面磁通密度 高斯[G]
EAXX EAXXA	②D					1	7	8	1	4.0 {0.40}	3000~3200
	10	M5×0.8	16	10	4	2	10	10	2	6.5 {0.66}	2900~3100
	12	M6×1.0									
	16	M8×1.25	18	11	5		12	14	3	8.0 {0.81}	2700~2900
	20	M10×1.5	20	13	6		14	17		17.7 {1.8}	2600~2800
	25	M10×1.5	22	15	8		14	22		35.0 {3.56}	2900~3100

■ 内螺纹型

型号		M×P (粗牙)	L	ℓ ₁	ℓ ₂	W	R	吸引力 N [kgf]	表面磁通密度 高斯[G]
EAXXH	②D	M4×0.7	15	9	4	8	1	4.0 {0.40}	3000~3200
	12	M4×0.7				10		6.5 {0.66}	2900~3100
	16	M5×0.8	17	10	5	14	2	8.0 {0.81}	2700~2800
	20	M5×0.8				17		17.7 {1.8}	2600~2800
	25	M6×1.0	18	11	6	22	3	35.0 {3.56}	2900~3100