



型号(①代码·②D) — ③V — ④T
EAHCW25 — 6 — 1

■ 请按步骤①~④选择型号和参数后进行订购。



型号区分: ④代碼 7天发货

■ 环型

EAHCW

磁化方向: 厚度方向

① N极划线或点

代码	材质	表面处理	耐热温度
EAHCW	钕磁铁	镀镍	80℃

型号		③V 选择	④T	吸引力 N {kgf}	表面磁通密度 高斯 [G]
①代码	②D				
EAHCW	6	2	2	6.2 {0.6}	2600~2800
			3	8.0 {0.8}	3200~3400
	8	3 4	1	4.9 {0.5}	1600~1800
			2	7.8 {0.8}	2600~2800
			3	9.8 {1.0}	3200~3400
	10	3 4 5 6	5	14.3 {1.5}	3200~3800
			1	6.9 {0.7}	1700~1900
			2	10.8 {1.1}	2600~2800
			3	11.8 {1.2}	3200~3400
	12	4 5 6 8	5	18.8 {1.9}	3600~3800
			1	7.8 {0.8}	1500~1700
			2	13.7 {1.4}	2500~2700
14	4 6 8	3	15.7 {1.6}	2900~3100	
		5	23.3 {2.4}	3600~3800	
		1	8.8 {0.9}	1600~1800	
18	6 8 12	2	19.6 {2.0}	2600~2800	
		3	23.5 {2.4}	2900~3100	
		5	36.0 {3.7}	3600~3800	
20	6 8 10 12	3	48.6 {5.0}	2900~3100	
		1	10.8 {1.1}	1300~1500	
		2	21.6 {2.2}	2200~2400	
25	6 8 10 12	3	33.3 {3.4}	2600~2800	
		5	62.3 {6.3}	3600~3800	
		1	12.7 {1.3}	1300~1500	
30	6 12 5	2	34.3 {3.5}	2100~2300	
		3	58.8 {6.0}	2600~2800	
		5	73.8 {7.5}	3400~3600	
			5	98.5 {10.0}	3000~3200



型号(①代码·②A) — ③B — ④T
EAMLN10 — 5 — 1

■ 请按步骤①~④选择型号和参数后进行订购。



型号区分: ④代碼 7天发货

■ 方型

代码	材质	表面处理	耐热温度
EAMLN	钕磁铁	镀镍	80℃
EAMLF	铁氧体磁铁	—	300℃

钕磁铁 EAMLN

磁化方向: 厚度方向

① N极划线或点

铁氧体磁铁 EAMLF

① N极划线或点

型号		③B	④T	吸引力 N {kgf}	表面磁通密度 高斯 [G]
①代码	②A				
EAMLN (钕磁铁)	3	3	3	2.8 {0.29}	4100~4300
			4	5.6 {0.57}	4300~4500
	5	5	5	8.9 {0.91}	4400~4600
			6	13.7 {1.4}	4500~4700
	10	8	8	23.2 {2.37}	4400~4600
			1	2.7 {0.28}	1700~1900
			2	8.5 {0.87}	3000~3200
			5	16.8 {1.71}	4200~4400
			1	6.5 {0.66}	1800~2000
			2	11.8 {1.2}	2500~2700
	15	10	8	39.3 {4.01}	4500~4700
			3	13.9 {1.42}	3100~3300
			5	23.7 {2.42}	4100~4300
			10	31.4 {3.2}	4700~4900
			3	23.9 {2.44}	2900~3100
			5	34.3 {3.5}	3300~3700
	20	10	10	61.4 {6.27}	4600~4800
			5	40.8 {4.16}	4600~4800
5			47.7 {4.87}	3500~3700	
10			77.8 {7.94}	4700~4900	
15			69.7 {7.11}	3300~3700	
20			84.8 {8.65}	3100~3300	
30	30	5	110.8 {11.31}	3300~3700	

型号		③B	④T	吸引力 N {kgf}	表面磁通密度 高斯 [G]	A公差	B公差
①代码	②A						
EAMLF (铁氧体磁铁)	10	5	5	1.6 {0.16}	900~1100	±0.1	±0.1
				4.9 {0.50}			
	20	10	5	9.8 {1.00}	1000~1200	±0.15	±0.15
				12.7 {1.30}			
	30	20	5	21.6 {2.20}	1100~1400	±0.15	±0.15
				29.4 {3.00}			
	40	30	10	17.7 {1.80}	1100~1400	±0.6	±1.2
				31.4 {3.20}			
						±0.8	±0.4
						±0.8	±0.8



邮箱: Service@srdfaa.com



传真: 0755-8957-5523

SRO仕瑞达